TESCON Vana® patch

Adhesive plaster for interior and exterior use



Technical data

	Material
Backing	Special PP fleece
Adhesive	Water-resistant SOLID adhesive
Release film	Siliconised paper

Property	Regulation	Value
Colour		Dark blue
Outdoor exposure		6 months
Bond durability, non-aged/aged	EN 17990	Passed
Can be plastered over		Yes
Application temperature		Above -10 °C ; +14 °F
Temperature resistance, permanent		-50 °C to 90 °C ; -60 °F to 194 °F
Storage		Cool and dry

Areas of application

For simple, quick and permanently sealed adhesion of blown-in insulation holes and for repairs.

Supply forms

Art. no.	Length	Width	Weight	Sales unit	Container	GTIN
10795	180 mm	180 mm	0.52 kg	1	288	4026639016560
10595	180 mm	180 mm	1.8 kg	1	144	4026639016553

Advantages

- ✔ Saves time: ready-to-install adhesive plaster, protruding release film is easy to remove
- ✔ Adheres reliably, even if moisture is present: water-resistant SOLID adhesive
- ✔ Flexible on-site work sequencing: 6 months of outdoor exposure
- ✔ Subsequent work can be started quickly: fleece backing can be plastered over directly
- ✔ Standards-compliant construction: for airtight sealing in accordance with DIN 4108-7, SIA 180 and RE 2020
- ✔ Excellent values in hazardous substance testing, has been tested according to the ISO 16000 evaluation scheme

Substrates

Clean subsurfaces before applying. Fine dust and any loose fibres must be thoroughly removed by vacuuming. Adhesion to frozen surfaces is not possible. There must be no water-repellent substances (e.g. grease or silicone) on surfaces where adhesives are to be applied. Subsurfaces must be sufficiently dry and stable; if necessary, subsurfaces should be stabilised or renewed.

Permanent adhesion is achieved on all pro clima internal and external membranes, other vapour control and airtight membranes (e.g. those made of PE, PA, PP and aluminium) as well as other roof and breather (WRB) membranes (e.g. those made of PP and PET).

Adhesive bonds are possible on planed and painted wood, hard plastics and metal (e.g. pipes, windows etc.), gypsum fibreboards, hard wood-based panels (chipboard, OSB, plywood, MDF and wood-fibre underlay panels).

Pre-treatment with TESCON PRIMER is required in the case of adhesion to wood-fibre underlay panels or on smooth, mineral subsurfaces. No pre-treatment with primer is required on gypsum fibreboards if their surfaces have been cleaned and are dust-free. It may be necessary to apply a bead of adhesive sealant – e.g. ORCON F – underneath the tape to achieve reliable seals on rougher surfaces.

Particular care is necessary when working with older or multi-layer subsurfaces. It is your responsibility to check the suitability of the subsurface; adhesion tests may be necessary in certain cases. Pre-treatment of the subsurface with TESCON PRIMER will improve the adhesive bond.

General conditions

The adhesive bonds should not be subjected to tensile strain. Rub the adhesive tapes firmly to secure the adhesive bonds. Ensure that there is sufficient resistance pressure. Windproof, airtight or rainproof sealing can only be achieved on vapour control membranes, roofing underlays or breather (WRB) membranes that have been laid without folds or creases. Ventilate continuously and systematically to prevent the build-up of excessive humidity; use a dryer if necessary.

Tested for hazardous substances according to ISO 16000

Made in Germany developed and produced by pro clima

The applications and conditions described here are based on current research findings and practical experience. We reserve the right to change the recommended application designs and installation methods and to develop and thus change the properties and quality of individual products. We would be glad to inform you about the current state of engineering knowledge at the time that your installation is carried out.

The planning documentation that is available from pro clima provides further information about installation methods and design details. If you have questions, please contact pro clima Technical Support in Germany at +49 6202 278245.

MOLL
bauökologische Produkte GmbH
Rheintalstraße 35 - 43
68723 Schwetzingen
Germany
Phone: +49 6202 2782 0
eMail: info@proclima.com