



Technical data

Material	
Sheet	Building paper, glued with PE
Reinforcement	Fibreglass mesh

Property	Regulation	Value
Colour		Blue
Surface weight	EN 1849-2	190 g/m ² ; 0.62 oz/ft ²
Thickness	EN 1849-2	0.23 mm ; 9 mils
Water vapour resistance factor μ	EN 1931	10 000
sd value	EN 1931	2.30 m
sd value, humidity-variable	EN ISO 12572	0.40 - 4 m
g value		11.5 MN·s/g
g value, humidity-variable		2 - 20 MN·s/g
Vapour permeance	ASTM E96	1.4 perms
Vapour permeance, humidity-variable	EN ISO 12572	0.82 - 8.2 US perms
Hydrosafe value (sd)	DIN 68800-2	2 m
Fire class	EN 13501-1	E
Watertightness to liquid water	EN 13984	NPD
Airtightness	EN 12114	Tested
Tensile strength MD/CD	EN 13859-1 (A)	550 N/5 cm / 420 N/5 cm ; 63 lb/in / 48 lb/in
Elongation MD/CD	EN 13859-1 (A)	5 % / 5 %
Nail tear resistance MD/CD	EN 13859-1 (B)	70 N / 70 N ; 16 lbf / 16 lbf
Durability after artificial ageing	EN 1296 / EN 1931	Passed
Temperature resistance	EN 1109, EN 1296, EN 1297	Permanent up to +40 °C ; +104 °F
Thermal conductivity		0.04 W/(m·K) ; 0.3 BTU-in/(h·ft ² ·°F)
CE labelling	EN 13984	Yes

Areas of application

Vapour check (alternate terms: vapour control or retarder) membrane for use on roofs, walls, ceilings and floors in combination with all fibrous insulation materials, including blown-in insulation, on structures that are open or closed to diffusion on the exterior, after appropriate design calculations.

Supply forms

Art. no.	GTIN	Length	Width	Contents	Weight	Sales unit	Container
10084	4026639011114	50 m	1.05 m	52.5 m ²	10 kg	1	42
10086	4026639011121	50 m	1.35 m	67.5 m ²	13 kg	1	42
10081	4026639011039	100 m	0.75 m	75 m ²	14 kg	1	24
10087	4026639011343	50 m	1.7 m	85 m ²	16 kg	1	42
10088	4026639011077	50 m	2.75 m	137.5 m ²	26 kg	1	20

Advantages

- ✓ Excellent protection against damage to structures and mould thanks to humidity-variable diffusion resistance
- ✓ Protected winter building sites thanks to hydrosafe® behaviour
- ✓ Can be combined with all fibrous insulation materials (including blown-in insulation)
- ✓ Ecological solution for sealing of the building envelope
- ✓ Excellent values in hazardous substance testing, has been tested according to the ISO 16000 evaluation scheme

General conditions

pro clima DB+ can be laid with the printed or unprinted side facing the installer, along or at a right angle to the sub-structure, for example, the rafters. It must not be laid and stretched tight.

If laid horizontally (at right angles to the sub-structure) then the maximum space permitted between the rafters is 1 m (3 ft). After laying, it is necessary to support the weight of the insulation with lathing on the inside. The laths should be no more than 65 cm (2' 2") apart. If, when using insulation mats and boards, for example, you expect tension as a result of the insulation weight on the adhesive tape joins, an additional supporting lath should be placed on the overlap. Alternatively, the adhesive tape can be reinforced along the overlap by sticking strips of adhesive tape at right angles to the overlap every 30 cm (1 ft).


Airtight seals can only be achieved on vapour control membranes that have been laid without folds or creases. Ventilate regularly to prevent excessive humidity (e.g. during the construction phase). Occasional rush/inrush ventilation is not adequate to quickly evacuate large amounts of construction-related humidity from the building. Use a dryer if necessary.

To prevent condensation, DB+ should be stuck down so that it is airtight immediately after installing the thermal insulation. This particularly applies when working in winter.

Additionally for blown-in insulation

DB+ can also be used as a membrane for all types of blown-in insulation. Its reinforcing layer prevents tearing when blowing in the insulation. If laid along the sub-structure it has the advantage that the overlap is supported on a firm foundation and is therefore protected.

To prevent condensation, the blown-in insulation should be introduced immediately after installing the airproofing layer. This particularly applies when working in winter.



Tested for hazardous substances according to



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about installation and design details is available in the pro clima planning documentation. If you have any questions, please contact [pro clima Technical Support](<https://proclima.com/service/technical-support>).

MOLL

bauökologische Produkte GmbH
Rheintalstraße 35 - 43
D-68723 Schwetzingen
Fon: +49 (0) 62 02 - 27 82.0
eMail: info@proclima.de