

SOLITEX FRONTA QUATTRO FB

Flame-resistant breather membrane (WRB) for open-jointed cladding, gap width up to 35 mm (1 3/8")



Technical data

		Material
Protective and covering fleece		Polypropylene microfibre
Membrane		Monolithic
Property	Regulation	Value
Colour		Black
Surface weight	EN 1849-2	145 g/m ² ; 0.48 oz/ft ²
Thickness	EN 1849-2	0.5 mm ; 20 mils
Water vapour resistance factor μ	EN ISO 12572	160
sd value	EN ISO 12572	0,08 m
g value		0.4 MN-s/g
Vapour permeance	ASTM E 96	41 perms
Fire rating	EN 13501-1	B - s1, d0
Outdoor exposure		6 months
Watertight joints with 'connect' adhesive strips or TESCON VANA tape	EN 13859-1	W1
Water column	EN ISO 811	10 000 mm ; 32' 10"
Watertightness, non-aged/aged*	EN 13859-2	W1 / W1
Tensile strength MD/CD	EN 13859-2 (A)	260 N/5 cm / 225 N/5 cm ; 30 lb/in / 26 lb/in
Tensile strength MD/CD, aged*	EN 13859-2 (A)	260 N/5 cm / 220 N/5 cm ; 30 lb/in / 25 lb/in
Elongation MD/CD	EN 13859-2 (A)	60 % / 80 %
Elongation MD/CD, aged*	EN 13859-2 (A)	30% / 40%
Nail tear resistance MD/CD	EN 13859-2 (B)	190 N / 220 N ; 43 lbf / 49 lbf
*) Durability after artificial ageing	EN 1297 / EN 1296	Passed (for walls with open joints)
Flexibility at low temperature	EN 1109	-40 °C ; -40 °F
Temperature resistance		Permanent -40 °C to 80 °C ; -40 °F to 176 °F
Thermal conductivity		0.04 W/(m·K) ; 0.3 BTU·in/(h·ft ² ·°F)
CE labelling	EN 13859-2	Yes

Areas of application

For use as a breather membrane (weather-resistant barrier, WRB) behind closed and open facades (open-jointed cladding up to a gap width of 35 mm (1 3/8")); cladding width = at least 3 x gap width). Installation onto boarding, wood-based panels and all mat or panel-shaped thermal insulation materials.

Supply forms

Art. no.	GTIN	Length	Width	Contents	Weight	Sales unit	Container
1AR02724	4026639227249	50 m	1.5 m	75 m ²	12 kg	1	20
1AR02726	4026639227263	50 m	3 m	150 m ²	24 kg	1	20

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about installation and design details is available in the pro clima planning documentation. If you have any questions, please contact [pro clima Technical Support](<https://proclima.com/service/technical-support>).

MOLL
bauökologische Produkte GmbH
 Rheinalstraße 35 - 43
 D-68723 Schwetzingen
 Phone: +49 (0) 62 02 - 27 82.0
 E-mail: info@proclima.com



Advantages

- ✓ Improved safety: 'not easily flammable', fire classification B-s1, d0 as per EN 13501-1
- ✓ Ensures reliable building components: highly permeable and, at the same time, maximum protection against driving rain
- ✓ Not visible behind open-jointed cladding: black fleece with identification marking in the overlap area
- ✓ Highest possible durability and thermostability thanks to the TEEE membrane
- ✓ 6 months of outdoor exposure

General conditions

SOLITEX FRONTA QUATTRO FB membranes should be installed with the black side facing outwards. The membranes are to be installed horizontally in a taut manner with no sagging.

When the product is used behind open-jointed cladding, the gap may be a maximum of 35 mm (1 3/8"). The width of cladding pieces must be at least three times the gap width. The distance between the open-jointed cladding and the membrane must be at least 20 mm (3/4").

Fasteners may not be applied in areas where water run-off is collected.

Additional measures (e.g. covering with tarpaulins) should be taken during the construction phase in the case of buildings that are lived in or buildings that are to be given particular protection. Covering with tarpaulins should also be considered if construction work is to be interrupted for a longer period.



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about installation and design details is available in the pro clima planning documentation. If you have any questions, please contact [pro clima Technical Support](<https://proclima.com/service/technical-support>).

MOLL
bauökologische Produkte GmbH
Rheintalstraße 35 - 43
D-68723 Schwetzingen
Phone: +49 (0) 62 02 - 27 82.0
E-mail: info@proclima.com

