



Technical data

| | | Material |
|--|-------------------|---|
| Protective and covering fleece | | Polypropylene |
| Functional film | | Polyethylene copolymer |
| Property | Regulation | Value |
| Colour | | Green |
| Surface weight | EN 1849-2 | 150 g/m ² ; 0.5 oz/ft ² |
| Thickness | EN 1849-2 | 0.45 mm ; 18 mils |
| Water vapour resistance factor μ | EN 1931 | 31 100 |
| sd value | EN 1931 | 14 m |
| sd value, humidity-variable | EN ISO 12572 | 0.25 - >25 m |
| g value | | 70 MN-s/g |
| g value, humidity-variable | | 1.25 - >125 MN-s/g |
| Vapour permeance | ASTM E96-A | 0.23 perms |
| Vapour permeance, humidity-variable | EN ISO 12572 | < 0.13 - 13 perms |
| Hydrosafe value (sd) | DIN 68800-2 | 2 m |
| Surface burning characteristics | ASTM E84 | Class A (Flame Spread 0; Smoke development index 105) |
| Fire class | EN 13501-1 | E |
| Outdoor exposure | | 2 months |
| Driving rain test | ZVDH | Passed |
| Watertight joints with 'connect' adhesive strips or TESCON VANA tape | EN 13859-1 | W1 |
| Watertightness to liquid water | EN 1928 | W1 |
| Water column | EN ISO 811 | > 2 500 mm ; > 8' 2" |
| Airtightness | EN 12114 | Tested |
| Tensile strength MD/CD | EN 12311-2 | 250 N/5 cm / 170 N/5 cm ; 29 lb/in / 19 lb/in |
| Elongation MD/CD | EN 12311-2 | 60% / 60% |
| Nail tear resistance MD/CD | EN 12310-1 | 120 N / 120 N ; 27 lbf / 27 lbf |
| Durability after artificial ageing | EN 1296 / EN 1931 | Passed |
| Temperature resistance | | Permanent -40 °C to 80 °C ; -40 °F to 176 °F |
| Thermal conductivity | | 0.04 W/(m·K) ; 0.3 BTU-in/(h·ft ² ·°F) |
| CE labelling | EN 13984 | Yes |

Areas of application

For use as a vapour check and airtight membrane that can be subjected to outdoor exposure over roof sheathing underneath over-rafter insulation in combination with all fibrous insulation materials on structures that are open or closed to diffusion on the exterior, e.g. flat/pitched roofs and green roofs, after appropriate design calculations have been carried out.

Advantages

- ✓ Best possible protection against moisture damage to structures thanks to humidity-variable diffusion resistance
- ✓ Protects buildings against the elements during the construction phase for roof pitches of 10° (2.1:12) and higher
- ✓ Protected winter building sites thanks to hydrosafe® behaviour
- ✓ Water-resistant and waterproof, can be walked on
- ✓ Excellent values in hazardous substance testing, has been tested according to the ISO 16000 evaluation scheme
- ✓ Quick and reliable adhesion thanks to the integrated 'connect' self-adhesive strips on the long edges of the membrane

General conditions

pro clima INTESANA connect should be installed with the printed side facing the installer. The membrane is to be installed horizontally (parallel to the eave) in a taut manner. The weight of the insulation must be supported by the cladding.

Airtight seals can only be achieved on vapour checks that have been fitted with no folds or creases. Ventilate regularly and systematically to prevent build-up of excessive humidity (e.g. during the construction phase). Occasional, intermittent ventilation is not sufficient to remove large quantities of moisture due to construction work from a building; use a dryer if necessary.

To avoid condensation formation, the thermal insulation should be installed immediately after airtight adhesion of INTESANA connect. This particularly applies when working in winter.

Fastening

- Overlap the membranes by at least 10 cm (4").
- Use fastening staples that are at least 10 mm (3/8") wide and 8 mm (5/16") long to attach the membranes. The membranes can only be fastened in a protected manner in the overlap area. The maximum distance between fasteners is 10 to 15 cm (4" to 6").



Tested for hazardous substances according to



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about installation and design details is available in the pro clima planning documentation. If you have any questions, please contact [pro clima Technical Support](<https://proclima.com/service/technical-support>).

MOLL

bauökologische Produkte GmbH

Rheintalstraße 35 - 43

D-68723 Schwetzingen

Fon: +49 (0) 62 02 - 27 82.0

eMail: info@proclima.de