# **SOLITEX MENTO® PLUS**

Reinforced roofing underlay



#### Technical data

|  | Material                        |  |  |  |  |
|--|---------------------------------|--|--|--|--|
| Protective and covering fleece                                       | Polypropylene micro             | fibre  |  |  |  |
| Functional film  | Monolithic TEEE                 |  |  |  |  |
| Reinforcement  | Polypropylene non-woven fabric  |  |  |  |  |
|  |                                 |  |  |  |  |
| Property   | Regulation                      | Value  |  |  |  |
| Colour   |                                 | Anthracite                                       |  |  |  |
| Surface weight   | EN 1849-2                       | 175 g/m² ; 0.57 oz/ft²                           |  |  |  |
| Thickness  | EN 1849-2                       | 0.60 mm ; 24 mils                                |  |  |  |
| Water vapour resistance factor $\boldsymbol{\mu}$                    | EN ISO 12572                    | 133  |  |  |  |
| sd value   | EN ISO 12572                    | 0.08 m   |  |  |  |
| g value  |                                 | 0.4 MN·s/g                                       |  |  |  |
| Vapour permeance   | ASTM E 96                       | 41 perms   |  |  |  |
| Fire class   | EN 13501-1                      | E  |  |  |  |
| Outdoor exposure   |                                 | 4 months   |  |  |  |
| Hail impact resistance   | VKF / AEAI                      | Class HR 5                                       |  |  |  |
| Watertight joints with 'connect' adhesive strips or TESCON VANA tape | EN 13859-1                      | W1   |  |  |  |
| Sarking/roofing underlay membrane<br>(Germany)                       | ZVDH-<br>Produktdatenblatt 2024 | USB / UDB  |  |  |  |
| Suitable as temporary roof covering<br>(Germany)                     | ZVDH                            | Yes  |  |  |  |
| Water column   | EN ISO 811                      | > 2 500 mm ; > 8' 2"                             |  |  |  |
| Watertightness, non-aged/aged*                                       | EN 13859-1                      | W1 / W1  |  |  |  |
| Tensile strength MD/CD   | EN 13859-1 (A)                  | 430 N/5 cm / 330 N/5 cm ;<br>49 lb/in / 38 lb/in |  |  |  |
| Tensile strength MD/CD, aged*  | EN 13859-1 (A)                  | 495 N/5 cm / 315 N/5 cm ; 57<br>Ib/in / 36 Ib/in |  |  |  |
| Elongation MD/CD   | EN 13859-1 (A)                  | 20% / 20%  |  |  |  |
| Elongation MD/CD, aged*  | EN 13859-1 (A)                  | 20% / 20%  |  |  |  |
| Nail tear resistance MD/CD   | EN 13859-1 (B)                  | 300 N / 300 N ; 67 lbf / 67 lbf                  |  |  |  |
| *) Durability after artificial ageing                                | EN 1297 / EN 1296               | Passed   |  |  |  |
| Flexibility at low temperature                                       | EN 1109                         | -40 °C ; -40 °F                                  |  |  |  |
| Fall-through protection  | GS-IFA-B03                      | Passed, even for freely<br>hanging membrane      |  |  |  |
| Temperature resistance   | EN 1109, EN 1296, EN<br>1297    | Permanent -40 °C to 100 °C ;<br>-40 °F to 212 °F |  |  |  |
| Thermal conductivity   |                                 | 0.04 W/(m·K) ; 0.3 BTU·in/<br>(h·ft²·°F)         |  |  |  |
|  |                                 | (ri·it²· F)                                      |  |  |  |

### Areas of application

For use as a diffusion-open roofing underlay over roof sheathing, MDF and wood-fibre underlay panels, and over all thermal insulation materials, including blown-in insulation materials.

#### Supply forms

| Art. no. | GTIN          | Length | Width | Contents | Weight  | Sales unit | Container |
|----------|---------------|--------|-------|----------|---------|------------|-----------|
| 12905    | 4026639129055 | 50 m   | 1.5 m | 75 m²    | 13.5 kg | 1          | 20        |
| 13758    | 4026639137586 | 50 m   | 3 m   | 150 m²   | 27 kg   | 1          | 20        |



#### Advantages

- Extremely robust thanks to reinforcement: suitable for blown-in insulation materials
- ✓ Flexible planning of construction schedules thanks to 4 months of outdoor exposure
- ✓ Well-protected building components: highly diffusion-open and maximum protection against driving rain and hail
- ✓ Dry building components: pore-free TEEE functional film actively transports moisture to the outside
- Permanent protection thanks to the high resistance to ageing and heat of the TEEE functional film
- Provides protection during the construction period: suitable as a temporary covering

## General conditions

SOLITEX MENTO membranes are to be installed with the printed side facing the installation technician. The membranes are to be installed as a roofing underlay membrane horizontally (parallel to the eave) in a taut manner with no sagging. Ensure that the subsurface is even when installing the membrane as a roofing underlay membrane. When the membrane is installed as a freely hanging underlay membrane, the rafter spacing is limited to 100 cm (3 ft).

Fasteners may not be applied in areas where water runs off in a collected manner (e.g. in roof valleys).

Ridge ventilation should be provided in the case of non-insulated attics that have not been converted. To do so, install the SOLITEX membrane in such a way that it stops 5 cm (2") before the ridge. In addition, permanent ventilation fittings should be provided in the unconverted attic. The membrane should be protected against the long-term impacts of UV radiation (e.g. by darkening windows).

The SOLITEX MENTO PLUS roofing underlay can be used as temporary covering for up to 4 months to protect the building structure during the construction phase in accordance with the regulations of the Central Association of the German Roofing Trade (ZVDH); in this case, the roof pitch must be at least 14° (approx. 3:12). Other national regulations may vary. The system components TESCON NAIDECK nail-sealing tape, ORCON F adhesive sealant and TESCON VANA are to be used for sealing of overlaps and joints. The connect variant has two self-adhesive strips for reliable external sealing. The specifications of the applicable national regulations are to be taken into account when carrying out installation and adhesion.

Under the regulations of the German Roofing Trade, these membranes are suitable as an additional measure for rain protection when installed as freely hanging underlay membranes with simple overlapping underneath roof tiles; when installed over timber sheathing as an underlay membrane with simple overlapping, SOLITEX MENTO membranes are also suitable as an additional measure for rain protection in the case of more demanding requirements.

#### Additional instructions for blown-in insulation materials

SOLITEX MENTO PLUS can also be used as a boundary layer for blown-in insulation materials of all types. It is recommended to use nail-sealing underneath the counter battens (e.g. TESCON NAIDECK). The battens must already be fitted before the blowing-in process is carried out. A protruding lath must be installed under the horizontal roof battens in the centre of the space between the rafters so that moisture occurring under the covering is drained off centrally between the rafters. This protruding lath should be at least 1 cm (3/8") thicker than the counter battens. It limits the bulging of the membranes during the blowing-in process and ensures the necessary cross-sectional area for ventilation.

If the insulation material is blown in from the outside, the blow-in holes can subsequently be taped over using TESCON VANA with a width of 15 cm (6").







The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

#### MOLL

bauökologische Produkte GmbH Rheintalstraße 35 - 43 D-68723 Schwetzingen Fon: +49 (0) 62 02 - 27 82.0 eMail: info@proclima.de Further information about installation and design details is available in the pro clima planning documentation. If you have any questions, please contact [pro clima Technical Support](https://proclima.com/service/technical-support).

