

SOLITEX WELDANO-S

Permeable, weldable roof lining strips



Technical data

		Substance
Membrane, both sides		Polyurethane
Substructure fleece		Polyester
Attribute	Regulation	Value
Colour		blue
Surface weight	EN 1849-2	310 ±15 g/m ² ; 1.02 ±0.05 oz/ft ²
Thickness	EN 1849-2	0.8 ±0.05 mm ; 31 ±2 mils
Water vapor resistance factor μ	EN ISO 12572	225
sd-value	EN ISO 12572	0.18 ±0.04 m
g-value		0.9 ±0.2 MN·s/g
Vapour permeance	ASTM E 96	18.2 US perms
Fire rating	EN 13501	E
Exposure time		3 months
Water column	EN 20811	> 4 000 mm ; > 13' 1"
Water tightness non-aged/aged*	EN 13859-1	W1 / W1
Tensile strength MD/CD	EN 13859-1 (A)	320 ±20 N/5 cm / 400 ±20 N/5 cm ; 37 ±2 lb/in / 46 ±6 lb/in
Tensile strength MD/CD aged*	EN 13859-1 (A)	275 ±20 N/5 cm / 320 ±20 N/5 cm ; 31 ±2 lb/in / 37 ±2 lb/in
Elongation MD/CD	EN 13859-1 (A)	50 ±10 % / 70 ±10 %
Elongation MD/CD aged*	EN 13859-1 (A)	50 ±10 % / 70 ±10 %
Nail tear resistance MD/CD	EN 13859-1 (B)	200 ±20 N / 200 ±20 N ; 45 ±4 lbf / 45 ±4 lbf
*) Artificial ageing by long term at 100 °C ; 212 °F	EN 1297 / EN 1296	passed
Flexibility at low temperature	EN 1109	-20 °C ; -4 °F
Temperature resistance		permanent -40 °C to 100 °C ; -40 °F to 212 °F
Thermal conductivity		2.3 W/(m·K) ; 16 BTU-in/(h·ft ² ·F)
CE labelling	EN 13859-1	available

Area of application

For reliable integration of counter battens into the SOLITEX WELDANO system.

Advantages

- ✓ Homogeneously weldable in the SOLITEX WELDANO system
- ✓ Also suitable for large counter battens
- ✓ Extremely high tear-resistance
- ✓ Permeable, airtight, rainproof and watertight
- ✓ Can be easily adapted for smaller dimensions using a knife or scissors

Substrates

Before adhesion, SOLITEX WELDANO should be wiped clean with a cloth.

Bonding to frozen membranes is not possible.

There must be no water-repellent substances (e.g. grease or silicone) on the membranes. Subsurfaces must be sufficiently dry and stable.

It is recommended that spot checks be performed to test the strength of the stuck joints.

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about the application and construction can be found in the pro clima planning documentation. For queries please call the pro clima technical hotline on +49 (0)6202 278245.

MOLL
bauökologische Produkte GmbH
Rheinalstraße 35 - 43
D-68723 Schwetzingen
Fon: +49 (0) 62 02 - 27 82.0
eMail: info@proclima.de



General conditions

SOLITEX WELDANO is to be installed horizontally (parallel to the eave). Unhindered drainage of water must be ensured. Cross joints are to be avoided. If membrane joints are necessary, they should be offset with respect to each other.

To protect the building structure during the construction phase, SOLITEX WELDANO roof lining membranes can be subjected to outdoor exposure for up to 3 months (e.g. as a temporary covering in accordance with ZVDH ('Zentralverband des Deutschen Dachdeckerhandwerks' - National Association of the German Roofing Trade).

The roof pitch must be at least 5°. National regulations should be taken into account here.

Fasteners should not be applied on flat surface areas or in areas where water run-off is collected (e.g. in roof valleys). We recommend the use of corrosion-resistant fasteners.

The membrane edges are to be welded using the WELDANO TURGA system solvent welding agent or a hot air gun. The welding area must be dry and free of frost, dust and grease. If dirt (e.g. oil) is stuck to the surface, moisten a cloth lightly with WELDANO TURGA system solvent welding agent and use it to clean off this dirt. Both sides of the membrane can be welded and are suitable as upper layers.

Welding with a solvent welding agent can be carried out at temperatures above 0 °C / 32 °F. Please observe the hazard notices on the container.

If a hot air gun is being used, we recommend a temperature of around 220 to 280 °C (430 to 530 °F) depending on the ambient temperature and wind conditions. Test this setting by carrying out a test weld on a sample piece of membrane. A 40 mm (1.6") nozzle width has been found to be suitable in practice for welded joints between surface membranes. A 20 mm (.8") nozzle may be more suitable in certain cases for more intricate joints.

The WELDANO ROFLEX pipe grommet is suitable for pipe diameters of 90 mm to 125 mm (3.5"-5") for roof pitches between 5° and 25°.

The WELDANO ROFLEX PLUS pipe grommet is suitable for pipe diameters of 90 mm to 120 mm (4.5"-4.75") for roof pitches up to 50°.

As an alternative to the use of the WELDANO ROFLEX, WELDANO INVEX or WELDANO INCAV system shaped elements, these elements can also be made by cutting appropriate shapes out of SOLITEX WELDANO membranes.

Important: The enclosed counter battens on the waterproof roof lining must be dry and chamfered on their upper side (≥ 3 mm; 120 mils) when they are installed. Ideally, structural timber should be used.

Additional technical information for Germany:

Depending on the requirements demanded of the roof lining when used as an additional measure, the roof lining can be installed to be rainproof or watertight (in accordance with ZVDH). Rainproof roof lining: The counter battens are installed over the roof lining membrane. Waterproof roof lining: The counter battens are integrated into the sealing layer. The roof lining membrane is installed over the counter battens here or else SOLITEX WELDANO-S sealing strips are fitted over the counter battens and welded to the roof lining membrane on both sides.

Ridge ventilation is permitted in the case of a rainproof roof lining. The roof lining membrane should then stop 30 mm (1.2") before the apex of the ridge. Cover the ventilation opening with a membrane strip over the counter batten along the ridge axis. Ridge ventilation is not permitted in the case of a waterproof roof lining.

The SOLITEX WELDANO roof lining membrane is to be bonded in a windproof and waterproof manner at the eave flashing. The eave flashing can be installed as a drip board under the gutter or as a guide board that guides water into the gutters. To protect the roof lining membrane from direct sunlight on a permanent basis, the width of the eave flashing should be selected appropriately depending on the roof pitch and the orientation of the building structure.



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about the application and construction can be found in the pro clima planning documentation. For queries please call the pro clima technical hotline on +49 (0)6202 278245.

MOLL
bauökologische Produkte GmbH
Rheintalstraße 35 - 43
D-68723 Schwetzingen
Fon: +49 (0) 62 02 - 27 82.0
eMail: info@proclima.de

