

# SOLITEX FRONTA® QUATTRO

Breather membrane (WRB) for open-jointed cladding, gap width up to 35 mm (1 3/8")



## Technical data

Material	
Protective and covering fleece	Polypropylene microfibre
Functional film	Monolithic TEEE

Property	Regulation	Value
Colour		Black
Surface weight	EN 1849-2	180 g/m <sup>2</sup> ; 0.59 oz/ft <sup>2</sup>
Thickness	EN 1849-2	0.60 mm ; 24 mils
Water vapour resistance factor $\mu$	EN ISO 12572	80
sd value	EN ISO 12572	0.05 m
g value		0.25 MN-s/g
Vapour permeance	ASTM E 96	65.6 perms
Fire class	EN 13501-1	E
Outdoor exposure		6 months
Watertight joints with 'connect' adhesive strips or TESCON VANA tape	EN 13859-1	W1
Water column	EN ISO 811	10 000 mm ; 32' 10"
Watertightness, non-aged/aged*	EN 13859-2	W1 / W1
Tensile strength MD/CD	EN 13859-2 (A)	290 N/5 cm / 220 N/5 cm ; 33 lb/in / 25 lb/in
Tensile strength MD/CD, aged*	EN 13859-2 (A)	200 N/5 cm / 135 N/5 cm ; 23 lb/in / 15 lb/in
Elongation MD/CD	EN 13859-2 (A)	50% / 70%
Elongation MD/CD, aged*	EN 13859-2 (A)	30% / 40%
Nail tear resistance MD/CD	EN 13859-2 (B)	220 N / 300 N ; 49 lbf / 67 lbf
*) Durability after artificial ageing	EN 1297 / EN 1296	Passed (for walls with open joints)
Flexibility at low temperature	EN 1109	-40 °C ; -40 °F
Temperature resistance	EN 1109, EN 1296, EN 1297	Permanent -40 °C to 100 °C ; -40 °F to 212 °F
Thermal conductivity		0.04 W/(m·K) ; 0.3 BTU-in/(h·ft <sup>2</sup> ·°F)
CE labelling	EN 13859-2	Yes

## Areas of application

For use as a breather membrane (weather-resistive barrier, WRB) behind closed and open facades (open-jointed cladding up to a gap width of 35 mm (1 3/8")); cladding width = at least 3 x gap width). Installation onto boarding, wood-based panels and all mat or panel-shaped thermal insulation materials.

## Supply forms

Art. no.	GTIN	Length	Width	Contents	Weight	Sales unit	Container
12933	4026639129338	50 m	1.5 m	75 m <sup>2</sup>	13.5 kg	1	20
13729	4026639137296	50 m	3 m	150 m <sup>2</sup>	27 kg	1	20

## Advantages

- ✓ Well-protected building components: highly permeable and, at the same time, maximum protection against driving rain
- ✓ Dry building components: pore-free TEEE functional film actively transports moisture to the outside
- ✓ Not visible behind open-jointed cladding: black fleece with printed marking only in the overlap area
- ✓ Highest possible durability and thermostability thanks to the TEEE functional film
- ✓ 6 months of outdoor exposure

## General conditions

SOLITEX FRONTA QUATTRO membranes should be installed with the black side facing outwards. The membranes are to be installed horizontally in a taut manner with no sagging.

When the product is used behind open-jointed cladding, the gap may be a maximum of 35 mm (1 3/8"). The width of cladding pieces must be at least three times the gap width. The distance between the open-jointed cladding and the membrane must be at least 20 mm (3/4").

Fasteners may not be applied in areas where water run-off is collected.

Additional measures (e.g. covering with tarpaulins) should be taken during the construction phase in the case of buildings that are lived in or buildings that are to be given particular protection. Covering with tarpaulins should also be considered if construction work is to be interrupted for a longer period.



---

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about installation and design details is available in the pro clima planning documentation. If you have any questions, please contact [pro clima Technical Support](<https://proclima.com/service/technical-support>).

---

### MOLL

**bauökologische Produkte GmbH**  
Rheintalstraße 35 - 43  
D-68723 Schwetzingen  
Fon: +49 (0) 62 02 - 27 82.0  
eMail: [info@proclima.de](mailto:info@proclima.de)